



SLIP REDUCER 300GRAMS TECHNICAL DATA SHEET

HI-TECH SLIP REDUCER waxes are micronized polypropylenes that are manufactured using special equipment to provide a unique texturing agent. The particle size is carefully controlled to produce a uniform textured surface in sealers & coatings. HI-TECH SLIP REDUCER will also impart a smoother “feel” than other types of texturing agents due to its rounded, almost spherical shape. The maximum particle size is controlled using screens.

The physical properties of polypropylene make HI-TECH SLIP REDUCER ideally suited as a texturing agent.

The low density and insolubility characteristics of HI-TECH SLIP REDUCER will reduce or eliminate settling and provide optimum performance in aromatic systems. The high melting point of HI-TECH SLIP REDUCER will insure a consistent texture even at high baking temperatures.

The rounded shape of HI-TECH SLIP REDUCER will provide optimum abrasion resistance, gloss control and will be less abrasive when compared to silica texturizing agents.

HI-TECH SLIP REDUCER

TYPICAL PROPERTIES	20	50	100S	140S	200S	200SF	270S	325S
Melting Point °P (ASTM D-127)	330-335	330-335	320-338	320-338	320-338	320-338	320-338	320-338
Melting Point °P (ASTM D-127)	166-168	166-168	160-170	160-170	160-170	160-170	160-170	160-170
Density @ 25 °C g/cc	0.90	0.90	0.86	0.86	0.86	0.86	0.86	0.86
Screen Analysis: Maximum Particle Size (microns)	840 (20 mesh)	300 (50 mesh)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)	74 (200 mesh)	53 (270 mesh)	44 (325 mesh)
Microtrac Laser Analysis: Mean Particle Size (microns)	N/A	160-180	80-100	45-55	35-45	25-35	15-25	11-15

HI-TECH SLIP REDUCER is recommended for use in industrial paints, lacquers and coatings (e.g wood, metal, powder or sprayed). The level of addition depends on the degree of texture desired. Usually adding 5-10% based upon resin solids of HI-TECH SLIP REDUCER will give a moderate textured finish.

Since HI-TECH SLIP REDUCER can be easily dispersed into all types of paints and coatings using a high speed mixer, the need for pre-dispersion is eliminated.

N/A – Not Applicable

Rev. 3/07

NOT CLASSIFIED AS HAZARDOUS MATERIAL ACCORDING TO WORKSAFE AUSTRALIA.

The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Hi-Tech Stencilcrete P/L disclaims any liability incurred in connection with the use of these data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe or any existing patents covering any material or its use.

Certified to ISO 9001:2000

HI-TECH STENCILCRETE P/L 6B CASSOLA PLACE, PENRITH NSW 2750 AUSTRALIA –
PH: 61 2 4731 4862, FAX: 61 2 4721 1706

www.htech.com.au

info@htech.com.au